

Product Feature :

“SOFT” is a thermoplastic polyurethane elastomer. It has good transparency, good mechanical properties, Good heat resistance, humidity resistance, and excellent flexibility under very low temperature. It is both an injection and extrusion molding grade for high-end products.

Applications:

Wire & cable, high pressure oil tubes, conveyor belts, shoes, seals, screen packs, etc.

Product Propert:

Typical Properties	Test Method	Unit	Typical values*
Form	N/A	-	Pellet
Color	N/A	-	Transparent
Hardness	ASTM D-2240	Shore A	70
Gravity	ASTM D-792	g/cm3	1.18
100% Modulus of elasticity	ASTM D412	MPa	5
Tensile Stress	ASTM D-412	MPa	30
Tear Strength	ASTM D-624	N/mm	100
Ultimate Elongation	ASTM D-412	%	550
DIN Abrasion	ISO 4649	mm3	60
Yellow Index	ASTM E313	--	7


*All these physical properties are based on injection molded samples, which are conditioned at 23 °C/50% for 24h. Above values are typical values and should not be used as specifications.

Processing Guidelines :

Injection Moulding Guideline

Mold Shrinkage:	0.015 ~ 0.025 inch/inch
Injection Speed:	Medium-Fast
Injection Pressure:	Medium-Fast
Back Pressure:	Low-Medium
Holding Pressure:	Sufficient to pack the mould
Cooling:	Can be demoulded when part have sufficiently cooled


Barrel Temperature (°C)



Extrusion Guidelines:

L/D Ration:	20:1 – 25:1
Compression Ratio:	2.5 – 3.0
Breaker Plate/Screen:	Both should be used
Draw Down:	5 – 10%
Cooling:	Cold water bath

Barrel Temperature (°C)



Processing Notes:

- A、 Drying before processing, it is recommended to dry for 3-5 hours at 80 degrees centigrade. If it is damp, the drying time will be lengthened.
- B、 Cleaning the screw and die with PP or PE before and after processing.
- C、 The gate and runner can be recycled, but less than 15%.
- D、 PE/EVA base color masterbatch is better for coloring.

The information and suggestions contained in this bulletin are to the best of our knowledge, accurate and reliable, but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller’s suggestions. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described